

DIEPA X53 K

Ordinary Lay
Non-rotation resistant wire rope

Nom. Diam. mm	Metall. Cross Section mm ²	Approx. Weight kg/ 100 m	Calculated Breaking Force			Minimum Breaking Force		
			1770 N/mm ² kN	1960 N/mm ² kN	2160 N/mm ² kN	1770 N/mm ² kN	1960 N/mm ² kN	2160 N/mm ² kN
6,5	22,0	20	38,9	43,2	47,5	33,1	36,7	39,9
8	36,2	33	64,1	71,0	78,1	54,5	60,4	65,6
10	55,1	50	97,5	108	119	82,9	91,8	99,7
11	70,4	63	125	138	152	106	117	128
14	107,4	97	190	211	232	162	179	195
15	126,4	114	224	248	273	190	211	229
18	171,8	155	304	337	371	258	286	312

Tolerance + 4%

Nom. Diam. mm	Strand Construction
6,5	8 x 19 Seale
8	8 x 19 Seale
10	8 x 19 Seale
11	8 x 19 Seale
14	8 x 19 Seale
15	8 x 26 Warrington-Seale
18	8 x 26 Warrington-Seale

